

VEROTEX INDUSTRIES B.V.
Edisonweg 3
5466 AR Veghel
Netherlands



Your notice of
26-10-2017

Your reference

Date
01-12-2017

Analysis Report 17.06202.02

Required tests :

EN 13773 (2003)

Identification number	Information given by the client	Date of receipt
T1723377	CORTINA FR 9910	26-10-2017

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1723377 - CORTINA FR 9910

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test 10-11-2017
Standard used EN 1101 (1995) + A1 (2005)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s

Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s

Reference: T1723377 - CORTINA FR 9910

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 14-11-2017
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	130	125	125
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	150	135	135	145
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 **Class 1**