

FLAMMABILITY TEST REPORT

Report No.: LEHTX00879731

Date Received: 19/04/16

Date Tested: 25/04/16

Date Issued: 25/04/16

Company Name & Address: VEROTEX INDUSTRIES
EDISONWEG 3
5466 AR VEGHEL
NETHERLANDS

Contact Name:

Sample Details

Reference No.: Not stated
Order No.: Not stated
Style No.: Not stated
Batch No.: Not stated
Quality: XFR - Gosh
Colour: Not stated
Supplier: Verotex Industries
Intended Use: Curtains, Upholstery, Bedding, Pillows
Fibre Composition: 100% Polyester inherent FR + crib 5 finish
Sample Description: Blue coloured woven fabric with white coloured backing

Test Method	Pre Treatment	Requirement	Result
BS 5852: 2006 Clause 11 (Upholstery Composite) Ignition source 5 (Crib 5)	Watersoak as Annex E of BS 5852: 2006	BS 5852: 2006 Clause 11 (Upholstery Composite) Ignition source 5 (Crib 5)	NI/5 (PASS)
The upholstered composite tested meets the performance requirements for resistance to ignition as detailed in the Medium Hazard (Crib 5 only) category of Table 1 in Clause 4 of BS 7176: 2007.			

Note: The customer requested that RX36110 foam with an approximate density 35 kg/m³ be used as the filling material

Sampling and frequency of testing

Each upholstery composite shall be tested in accordance with the relevant tests identified in Table 1 for the appropriate hazard category every 2 500 units produced or once per month. Retesting shall be carried out where there is any major basic alteration to a furniture specification (e.g. of fibre content, construction, flame-retardant finish or mass per unit area of fabric, density or type of filling or change of materials manufacturer). Changes in the colour (where the fabric was flame-retardant finished in the same batch) of the product or minor changes in the pattern or construction, e.g. of the order of 2 picks/cm, shall not be deemed sufficient reason to necessitate retesting.

.....
STEVEN OWEN
(Chemical Technologist)

.....

ANDREW HALLETT
(Flammability Team Leader)

.....
CAROLE SPOWART
(Flammability Technician)

.....
SIMON CHEE
(Operations Manager)

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS 5852:2006 Clause 11 (upholstery composite) Ignition source 5

Foam specification

Supplier / Grade: Carpenter / RX36110 (As requested by the customer)
Size: 450 x 450 x 75mm (back) & 450 x 300 x 75mm (seat)
Density / Hardness: 34-36kg/m³ /105-115N

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 24 hours in an atmosphere having a temperature of 23 ± 2°C and a relative humidity of 50 ± 5%

At Time of Testing: Temperature of 10 °C to 30 °C and a relative humidity of 15 % to 80 %

Test Results

"The following test results relate only to the ignitability of the combination of upholstery composites (BS 5852: 2006, Clause 11) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use";

Test number / position	1		2	
Criterion of Ignition				
Smouldering Criteria				
Externally detectable amounts of smoke, heat or glowing 60 minutes after crib ignition	No		No	
Escalating smouldering behaviour rendered the test unsafe to continue and required forcible extinction	No		No	
Smouldering essentially consumed the test specimen within the duration of the test / Smouldering reached the extremities of the test specimen (Other than the top of the vertical part of the test specimen) within the duration of the test	No		No	
Flaming Failure				
The test specimen continued to flame for more than 10 minutes after the ignition of the crib	No		No	
Escalating combustion behaviour rendered the test unsafe to continue and required forcible extinction	No		No	
Flaming essentially consumed the test specimen within the duration of the test	No		No	
Flaming reached the extremities of the test specimen (Other than the top of the vertical part of the test specimen) within the duration of the test	No		No	
Debris from the test specimen caused an isolated floor fire that continued to flame for more than 10 minutes after the ignition of the crib	No		No	
Final Examination				
Progressive smouldering was observed when the sample was dismantled	No		No	
Evidence of charring within the filling (other than discolouration) more than 100mm in any direction, apart from upwards, from the nearest part of the original position of the ignition source	No		No	
Time to extinction of flames after crib ignition	5 Minutes 38 Seconds		5 Minutes 07 Seconds	
Time to extinction of glowing after crib ignition	7 Minutes 02 Seconds		6 Minutes 45 Seconds	
Time to extinction of smoke after crib ignition	7 Minutes 53 Seconds		7 Minutes 33 Seconds	
Maximum extent of damage to back (mm) Length / Width	400	80	400	130
Maximum extent of damage to base (mm) Length / Width	65	85	60	105
Test Result	NI/5 (PASS)		NI/5 (PASS)	
Ignitability performance index: "Clause 11 - NI/5"				

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.