

Report EN13773

Document number:

202201929

Report date:

26/09/2022

Fabric reference:

Jaipur

01-Metal

Date analyses:

26/09/2022

Customer:

Verotex Industries Edisonweg 3 5466 AR Veghel Netherlands Place analyses:

Labotex

Date of request:

15/06/2022

Samples received:

29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)*C and RH (65+-4)%

S					

Results

Remarks

!


Burning behaviour of fabrics for curtains drapes

EN13773

conditioning min 24h in standard atmosphere

used gas: propane flame height: 40mm bottom edge ignition: size EN1101: 200x80mm size EN13772: 560x170mm

flowchart EN13773



EN 1101

Test EN1101 is performed after subjecting the fabric to 1 washing cycle,

based on the recommended washing instructions.

flame application time	warp	weft
1s	no ignition	no ignition
2s	no ignition	no ignition
3s	no ignition	no ignition
4s	no ignition	no ignition
5s	no ignition	no ignition
10s	no ignition	no ignition
15s	no ignition	no ignition
20s	no ignition	no ignition
Mean ignition time warp:	0.0	
Mean ignition time weft:	0.0	
Minimum ignition time:	0.0	
5s 10s 15s 20s Mean ignition time warp: Mean ignition time weft:	no ignition no ignition no ignition no ignition 0.0	no ignition no ignition no ignition

Approval date: 19/04/2022



Report EN13773

Document number:

202201929

Report date:

26/09/2022

Fabric reference:

Jaipur

01-Metal

Date analyses:

26/09/2022

Customer:

Verotex Industries Edisonweg 3 5466 AR Veghel Netherlands Place analyses:

Labotex

Date of request:

15/06/2022

Samples received:

29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification

Results

Remarks

conditioning not according to standard

Approval date: 19/04/2022

1

EN13772 before wasi	hins	ê
---------------------	------	---

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	159	138	111	155
flaming debris	no	no	no	no
weft	face	reverse	face	face
weft 1st marker thread severed	face no	reverse no	face no	face no
1st marker thread severed	no	no	no	no
1st marker thread severed 2nd marker thread severed	no	no	no	no no
1st marker thread severed 2nd marker thread severed 3rd marker thread severed time to severance 3rd	no no	no no	no no	no no

EN13772 after washing

warp	face	reverse	reverse	reverse
1st marker thread severed	no	по	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	0	0	0	0
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	102	130	178	160
flaming debris	no	no	no	no
weft	face	reverse	face	face
weft 1st marker thread severed	face no	reverse no	face no	face no
	V	ñ	7	
1st marker thread severed	no	no	no	no
1st marker thread severed 2nd marker thread severed	no	no no	no no	no no
1st marker thread severed 2nd marker thread severed 3rd marker thread severed time to severance 3rd	no no 0	no no 0	no no	no no 0



Report EN13773

Document number:

202201929

Report date:

26/09/2022

Fabric reference:

Jaipur 01-Metal

Date analyses:

26/09/2022

Customer:

Verotex Industries Edisonweg 3

Place analyses:

Labotex

5466 AR Veghel Netherlands

Date of request:

15/06/2022

Samples received:

29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification

Results

Remarks

1

Classification

Class 1X Class 2 Class 3 Class 4 or 5



Approval date: 19/04/2022

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.

Annick Gijsemans - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be consulted on the BELAC website https://ng3.economie.fgov.be/Ni/belac/labotesting/applic/accreditedc_nl.asp7certificatienummer=364-TEST
Sampling is performed by the costumer. Fabric analysed as recieved. The results in this report only relate to the tested items.

Samples will be returned to the customer together with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report cannot be copied unless in its complete form and with written approval of Labotex (Kontich).

Uncertainty of measurement on the test result is not taken into account when assessing compliance with the specifications. When results are compliant to the specification, the square next to the result

is empty. When the result is not compliant to the specification, the square is filled with a flag "Y". The uncertainty and the description of the methods are available at the lab on request.

ANA00023