

# Report EN13773

Document number:

202201957

Report date:

10/10/2022

Fabric reference:

Jasmone

01-Silver

Date analyses:

10/10/2022

Customer:

Verotex Industries Edisonweg 3 5466 AR Veghel

Netherlands

Place analyses:

Date of request:

Labotex 15/06/2022

Samples received:

29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Burning behaviour of fabrics

Results

Remarks

1

for curtains drapes


Specification

EN13773

conditioning min 24h in standard atmosphere

used gas: propane flame height: 40mm bottom edge ignition: size EN1101: 200x80mm size EN13772: 560x170mm

## flowchart EN13773



#### EN 1101

Test EN1101 is performed after subjecting the fabric to 1 washing cycle,

based on the recommended washing instructions.

flame application time	warp	weft
<b>1</b> s	no ignition	no ignition
2s	no ignition	no ignition
3s	no ignition	no ignition
4s	no ignition	no ignition
5s	no ignition	no ignition
10s	no ignition	no ignition
15s	no ignition	no ignition
20s	no ignition	no ignition
Mean ignition time warp:	0.0	
Mean ignition time weft:	0.0	
Minimum ignition time:	0.0	

ANA00023 Page 1 of 3 Approval date: 19/04/2022



# Report EN13773

Document number:

202201957

10/10/2022 Report date:

Fabric reference:

**Customer:** 

Jasmone

01-Silver

Date analyses: Verotex Industries Place analyses: 10/10/2022

Edisonweg 3 5466 AR Veghel Netherlands

Labotex

15/06/2022 Date of request: Samples received: 29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification

Results

Remarks

EN13772 before washing					
warp	face	reverse	reverse	reverse	
1st marker thread severed	no	no	no	no	i my
2nd marker thread severed	no	no	no	no	
3rd marker thread severed	no	no	no	no	
time to severance 3rd marker thread (s)	0	0	0	0	
destroyed length (mm)	153	140	139	158	İ
flaming debris	no	no	no	no	
weft	face	reverse	face	face	
1st marker thread severed	no	no	no	no	
2nd marker thread severed	no	no	no	no	
3rd marker thread severed	no	no	no	no	
time to severance 3rd marker thread (s)	0	0	0	0	
destroyed length (mm)	146	138	163	150	į.
flaming debris	no	no	no	no	Ĭ

## EN13772 after washing

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	140	110	125	143
flaming debris	no	no	no	no
weft	face	reverse	face	face
weft  1st marker thread severed	face no	reverse	face no	face no
	4	id	i i	9
1st marker thread severed	no	no	no	no
1st marker thread severed 2nd marker thread severed	no	no no	no	no no
1st marker thread severed 2nd marker thread severed 3rd marker thread severed time to severance 3rd	no no	no no	no no	no no

ANA00023 Page 2 of 3 Approval date: 19/04/2022

XXXX
LABOTEX

Document number:

# Report EN13773

Report date:

10/10/2022

Fabric reference:	Jasmone			
	01-Silver	Date analyses:	10/10/2022	
54	Verotex Industries	Place analyses:	Labotex	
	Edisonweg 3 5466 AR Veghel	Date of request:	15/06/2022	
	Netherlands	Samples received:	29/06/2022	
Festing and conditioning in standard a	tmosphere, T (20+-2)°C and RH (65+-4	1)%		
Specification		Results	Remarks	Ĩ
	Classification			
	Class 1	Х		
	Class 2			
	Class 3		BBE	
	Class 4 or 5		LAC B645TEST	

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.

### Annick Gijsemans - Laboratory Manager

202201957

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be consulted on the BELAC website https://ng3.economie.fgov.be/Nil/belac/labotesting/applic/accreditedc\_nl.asp?certificatlenummer=364-TEST
Sampling is performed by the costumer. Fabric analysed as recieved. The results in this report only relate to the tested items.
Samples will be returned to the customer together with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report cannot be copied unless in its complete form and with written approval of Labotex (Kontich).

Uncertainty of measurement on the test result is not taken into account when assessing compliance with the specifications. When results are compliant to the specification, the square next to the result is empty. When the result is not compliant to the specification, the square is filled with a flag "V".

The uncertainty and the description of the methods are available at the lab on request.

ANA00023 Page 3 of 3 Approval date: 19/04/2022