



Textiles and Apparel Solutions Centre
The Warehouse, Brewery Lane, Leigh
Lancashire, WN7 2RJ, United Kingdom

Tel: +44 (0) 1942 265 700
Fax: +44 (0) 1942 670 788
www.intertek.com/consumergoods

FLAMMABILITY TEST REPORT

Report No.: LEI17020000745A Date Received: 09/02/17 Date Tested: 15/02/17 Date Issued: 15/02/17

Company Name & Address: VEROTEX INDUSTRIES
EDISONWEG 3
5466 AR VEGHEL
NETHERLANDS


Contact Name:

Sample Details

Order No.: Not stated
Reference No.: Not stated
Style No.: Not stated
Batch No.: Not stated
Quality: XFR - Jermian
Colour: Not stated
Supplier: Not stated
Intended Use: Curtains
Quoted Fibre Composition: 100% Polyester inherent FR
Retailer: Not stated
Buying Division: Not stated
Sample Description: Grey and cream coloured woven fabric

| Test Method | Pre Treatment | Flammability Performance Requirement | Result |
|-----------------------|--|--------------------------------------|--------|
| BS 5867: Part 2: 2008 | 50 Cycles of BS EN ISO 10528 (Standard Washing Procedure) @ 75°C and then low heat tumble dried. | Type C | PASS |

STEVEN OWEN
(Chemical Technologist)


ANDREW HALLETT
(Flammability Team Leader)

CAROLE SPOWART
(Flammability Technician)

SIMON CHEE
(Operations Manager)





Textiles and Apparel Solutions Centre
The Warehouse, Brewery Lane, Leigh
Lancashire, WN7 2RJ, United Kingdom

Tel: +44 (0) 1942 265 700
Fax: +44 (0) 1942 670 788
www.intertek.com/consumergoods

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS 5867: Part 2: 2008 Type B using BS EN ISO 15025:2002
(With the modifications from clause 6.3.2 of BS 5867: Part 2: 2008).

Ignition Source: 25mm horizontal reach Propane gas flame

Ignition Type: Surface

Flame Application Times: 5,15,20 & 30 Seconds

Sample Size: 200 x 160mm

Side Tested: Face & Back

Pre-treatment / Durability procedure

50 Cycles of BS EN ISO 10528 (Standard Washing Procedure) @ 75°C and then low heat tumble dried.

Conditioning

Prior to Testing: At least 24 hours in an atmosphere having a temperature of 20±2°C. and a relative humidity of 65±5%

At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 65%



FLAMMABILITY TEST REPORT**Test Results**

Report of tests carried out in accordance with BS EN ISO 15025:2002. The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Before wash

| Sample No. / Direction | Afterflame (Secs) | Afterglow (Secs) | Combined Mean (Secs) | | Flaming Debris | Flame To Edge | Hole To Edge |
|----------------------------------|----------------------|---------------------|----------------------|-----------|----------------|---------------|--------------|
| | | | Afterflame | Afterglow | | | |
| 5 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |
| 15 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |
| 20 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |
| 30 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |

After wash

| Sample No. / Direction | Afterflame (Secs) | Afterglow (Secs) | Combined Mean (Secs) | | Flaming Debris | Flame To Edge | Hole To Edge |
|----------------------------------|----------------------|---------------------|----------------------|-----------|----------------|---------------|--------------|
| | | | Afterflame | Afterglow | | | |
| 5 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |
| 15 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |
| 20 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |
| 30 second flame application time | | | | | | | |
| 1 Length (face) | 0.0 | 0.0 | 0.0 | 0.0 | No | No | No |
| 2 Width (face) | 0.0 | 0.0 | | | No | No | No |
| 3 Length (back) | 0.0 | 0.0 | | | No | No | No |
| 4 Width (back) | 0.0 | 0.0 | | | No | No | No |

Conclusions

The sample when tested meets the requirements of BS 5867: Part 2: 2008 Type C. **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.