



Report EN13773

Document number: 202201951 Report date: 29/09/2022
Fabric reference: Jorace
01-Niagara
Customer: Verotex Industries
Edisonweg 3
5466 AR Veghel
Netherlands
Date analyses: 29/09/2022
Place analyses: Labotex
Date of request: 15/06/2022
Samples received: 29/06/2022

Testing and conditioning in standard atmosphere, T (20±2)°C and RH (65±4)%

Specification	Results	Remarks	!
Burning behaviour of fabrics for curtains drapes	EN 1101		
	Test EN1101 is performed after subjecting the fabric to 1 washing cycle, based on the recommended washing instructions.	conditioning not according to standard	
EN13773			
conditioning min 24h in standard atmosphere	flame application time	warp	weft
used gas: propane	1s	no ignition	no ignition
flame height: 40mm	2s	no ignition	no ignition
bottom edge ignition:	3s	no ignition	no ignition
size EN1101: 200x80mm	4s	no ignition	no ignition
size EN13772: 560x170mm	5s	no ignition	no ignition
	10s	no ignition	no ignition
	15s	no ignition	no ignition
	20s	no ignition	no ignition
	Mean ignition time warp:	0.0	
	Mean ignition time weft:	0.0	
	Minimum ignition time:	0.0	
flowchart EN13773			



Report EN13773

Document number: 202201951 Report date: 29/09/2022
Fabric reference: Jorace
01-Niagara
Customer: Verotex Industries Date analyses: 29/09/2022
Edisonweg 3 Place analyses: Labotex
5466 AR Veghel Date of request: 15/06/2022
Netherlands Samples received: 29/06/2022

Testing and conditioning in standard atmosphere, T (20±2)°C and RH (65±4)%

Specification	Results				Remarks	!
<u>EN13772 before washing</u>						
warp	face	reverse	reverse	reverse		
1st marker thread severed	no	no	no	no		
2nd marker thread severed	no	no	no	no		
3rd marker thread severed	no	no	no	no		
time to severance 3rd marker thread (s)	0	0	0	0		
destroyed length (mm)	133	146	119	151		
flaming debris	no	no	no	no		
weft	face	reverse	face	face		
1st marker thread severed	no	no	no	no		
2nd marker thread severed	no	no	no	no		
3rd marker thread severed	no	no	no	no		
time to severance 3rd marker thread (s)	0	0	0	0		
destroyed length (mm)	119	132	122	160		
flaming debris	no	no	no	no		
<u>EN13772 after washing</u>						
warp	face	reverse	reverse	reverse		
1st marker thread severed	no	no	no	no		
2nd marker thread severed	no	no	no	no		
3rd marker thread severed	no	no	no	no		
time to severance 3rd marker thread (s)	0	0	0	0		
destroyed length (mm)	122	108	130	121		
flaming debris	no	no	no	no		
weft	face	reverse	face	face		
1st marker thread severed	no	no	no	no		
2nd marker thread severed	no	no	no	no		
3rd marker thread severed	no	no	no	no		
time to severance 3rd marker thread (s)	0	0	0	0		
destroyed length (mm)	131	145	132	146		
flaming debris	no	no	no	no		



Report EN13773

Document number:

202201951

Report date:

29/09/2022

Fabric reference:

Jorace

Date analyses:

29/09/2022

Customer:

01-Niagara

Place analyses:

Labotex

Verotex Industries

Date of request:

15/06/2022

Edisonweg 3

Samples received:

29/06/2022

5466 AR Veghel

Netherlands

Testing and conditioning in standard atmosphere, T (20±2)°C and RH (65±4)%

Specification	Results	Remarks	!
Classification			
Class 1	X		
Class 2			
Class 3			
Class 4 or 5			



Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.

Annick Gijsemans - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be consulted on the BELAC website https://ng3.economie.fgov.be/NL/belac/labotesting/applc/accreditedc_nl.asp?certificatienummer=364-TEST

Sampling is performed by the customer. Fabric analysed as received. The results in this report only relate to the tested items.

Samples will be returned to the customer together with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report cannot be copied unless in its complete form and with written approval of Labotex (Kontich).

Uncertainty of measurement on the test result is not taken into account when assessing compliance with the specifications. When results are compliant to the specification, the square next to the result is empty. When the result is not compliant to the specification, the square is filled with a flag "V".

The uncertainty and the description of the methods are available at the lab on request.