

# Report EN13773

Date analyses:

Place analyses:

Date of request:

Samples received:

Document number: Fabric reference:

202201909

Report date:

Joyce

01-Metal

**Customer:** Verotex Industries Edisonweg 3

10/10/2022 Labotex

10/10/2022

5466 AR Veghel

Netherlands

15/06/2022

29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

**Specification** 

Results

Remarks


**Burning behaviour of fabrics** for curtains drapes

EN13773

conditioning min 24h in standard atmosphere

used gas: propane flame height: 40mm bottom edge ignition: size EN1101: 200x80mm size EN13772: 560x170mm

## flowchart EN13773



### EN 1101

Test EN1101 is performed after subjecting the fabric to 1 washing cycle,

based on the recommended washing instructions.

flame application time	warp	weft
<b>1s</b>	no ignition	no ignition
2s	no ignition	no ignition
3s	no ignition	no ignition
4s	no ignition	no ignition
5s	no ignition	no ignition
10s	no ignition	no ignition
15s	no ignition	no ignition
20s	no ignition	no ignition
Mean ignition time warp:	4.4	
Mean ignition time weft:	0.0	
Minimum ignition time:	0.0	

ANA00023 Page 1 of 3 Approval date: 19/04/2022



# Report EN13773

Document number:

202201909 Joyce

Report date:

10/10/2022

Fabric reference:

**Customer:** 

01-Metal

10/10/2022

Verotex Industries Edisonweg 3 5466 AR Veghel Netherlands

Place analyses: Date of request:

Date analyses:

Labotex 15/06/2022

122

Samples received: 29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification

Results

Remarks

EN13772 before washing

14/0.55	face			
warp	Tace	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	129	141	140	159
flaming debris	no	no	no	no
weft	face	reverse	face	face
1st marker thread severed	no	no	no	no
	no no	no	no no	no
1st marker thread severed 2nd marker thread severed 3rd marker thread severed				no
2nd marker thread severed	no	no	no	
2nd marker thread severed 3rd marker thread severed time to severance 3rd	no no	no no	no no	no

## EN13772 after washing

destroyed length (mm)

flaming debris

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	110	132	122	129
flaming debris	no	no	no	no
weft	face	reverse	face	face
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0

154

no


123

no

146

no

ANA00023 Page 2 of 3 Approval date: 19/04/2022



<b>XXXX</b>
LABOTEX

# Report EN13773

Document number:	202201909	Report date:	10/10/2022
Fabric reference:	Joyce		
	01-Metal	Date analyses:	10/10/2022
Customer:	Verotex Industries	Place analyses:	Labotex
	Edisonweg 3 5466 AR Veghel	Date of request:	15/06/2022
	Netherlands	Samples received:	29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification		Results	Remarks !
Classin	fication		
	Class 1	Х	
	Class 2		
	Class 3		B E
	Class 4 or 5		LAC 364-TEST

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.



#### Annick Gijsemans - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be consulted on the BELAC website https://ng3.economie.fgov.be/Nil/belac/labotesting/applic/accreditedc\_nl.asp?certificatienummer=364-TEST
Sampling is performed by the costumer. Fabric analysed as recleved. The results in this report only relate to the tested items.
Samples will be returned to the customer together with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.
This report cannot be copied unless in its complete form and with written approval of Labotex (Kontich).
Uncertainty of measurement on the test result is not taken into account when assessing compliance with the specifications. When results are compliant to the specification, the square next to the result is empty. When the result is not compliant to the specification, the square is filled with a flag "y".

The uncertainty and the description of the methods are available at the lab on request.

ANA00023 Page 3 of 3 Approval date: 19/04/2022