

Report EN13773

Date of request:

Samples received:

Document number: Fabric reference:

202201931 Juniper

01-Mineral

Report date:

11/10/2022

Customer:

Verotex Industries Edisonweg 3

Date analyses: Place analyses: 11/10/2022

5466 AR Veghel

Labotex 15/06/2022

Netherlands

29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Burning behaviour of fabrics for curtains drapes


conditioning min 24h in

Specification

EN13773

standard atmosphere used gas: propane flame height: 40mm bottom edge ignition: size EN1101: 200x80mm size EN13772: 560x170mm

flowchart EN13773



EN 1101

Test EN1101 is performed after subjecting the fabric to 1 washing cycle,

based on the recommended washing instructions.

Minimum ignition time:

Results

conditioning not according to standard

Remarks

flame application time weft no ignition 1s no ignition 2s no ignition no ignition 3s no ignition no ignition 4s no ignition no ignition 5s no ignition no ignition 10s no ignition no ignition 15s no ignition no ignition 20s no ignition no ignition Mean ignition time warp: 0.0 Mean ignition time weft: 0.0

0.0

ANA00023 Page 1 of 3 Approval date: 19/04/2022



Report EN13773

Document number:

202201931

Report date: 11/10/2022

Fabric reference:

Juniper 01-Mineral

Date analyses:

11/10/2022

Customer:

Verotex Industries Edisonweg 3 5466 AR Veghel Place analyses:

Date of request:

Labotex 15/06/2022

Netherlands Samples received: 29/06/2022

Testing and conditioning in standard atmosphere, T (20+-2)°C and RH (65+-4)%

Specification

Results

Remarks

1

EN13772 before washing

EN13//2 Detore washing				
warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	140	122	167	165
flaming debris	no	no	no	no
weft	face	reverse	face	face
weft 1st marker thread severed	face	reverse no	face no	face
1st marker thread severed	no	no	no	no
1st marker thread severed 2nd marker thread severed	no	no	no	no no
1st marker thread severed 2nd marker thread severed 3rd marker thread severed time to severance 3rd	no no no	no no	no no	no no

EN13772 after washing

destroyed length (mm)

flaming debris

warp	face	reverse	reverse	reverse
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0
destroyed length (mm)	132	111	106	140
flaming debris	no	no	no	no
weft	face	reverse	face	face
1st marker thread severed	no	no	no	no
2nd marker thread severed	no	no	no	no
3rd marker thread severed	no	no	no	no
time to severance 3rd marker thread (s)	0	0	0	0

129

130

114

ANA00023 Page 2 of 3 Approval date: 19/04/2022

117

no

XXXX
LABOTEX

Document number:

Report EN13773

Report date:

11/10/2022

Fabric reference:	Juniper			
	01-Mineral	Date analyses:	11/10/2022	
Customer:	Verotex Industries	Place analyses:	Labotex	
	Edisonweg 3 5466 AR Veghel Netherlands	Date of request:	15/06/2022 29/06/2022	
		Samples received:		
Testing and conditioning in standard	atmosphere, T (20+-2)°C and RH (65+-4	1)%		
Specification		Results	Remarks	1
	Classification			
	Class 1	хх		
	Class 2			
	Class 3	******************	B B	
	Class 4 or 5		LAC 364-TEST	

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.

Annick Gijsemans - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be consulted on the BELAC website https://ng3.economie.fgov.be/Nl/belac/abotesting/applic/accreditedc_nl.asp?certificatienummer=364-TEST
Sampling is performed by the costumer. Fabric analysed as recieved. The results in this report only relate to the tested items.
Samples will be returned to the customer together with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year

202201931

samples will be returned to the customer together with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report cannot be copied unless in its complete form and with written approval of Labotex (Kontich).

Uncertainty of measurement on the test result is not taken into account when assessing compliance with the specifications. When results are compliant to the specification, the square next to the result is empty. When the result is not compliant to the specification, the square is filled with a flag "v".

The uncertainty and the description of the methods are available at the lab on request.

ANA00023 Page 3 of 3 Approval date: 19/04/2022