



Report IMO FTP Code Part 7

Document number: 202302056 Report date: 10/07/2023
Fabric reference: Obay
Date analyses: 10/07/2023
Fabric composition: 01-Duckegg (BPZ-012525 BABK)
Place analyses: Labotex
Customer: Verotex Industries
Edisonweg 3
5466 AR Veghel
Netherlands
Date of request: 3/07/2023
Samples received: 3/07/2023

Testing and conditioning in standard atmosphere, T (20±2)°C and RH (65±4)%

Specification Results Remarks

IMO fire test procedure

Resolution 2010
FTP Code Part 7

conditioning min 24h. in
standard atmosphere
sample size: (220 x 170) mm
used gas: propane
flame application: 5s - 15s

The test specimen have not been cleaned nor submitted to an accelerated ageing process

Indicative weight 405 g/m²
Indicative thickness 0.74 mm

a. Determination of the worst testing conditions

warp	surface ignition		edge ignition	
	1	2	3	4
flame application time (s)	5	15	5	15
afterflame time (s)	0	0	0	0
propagation length flame surface flash (mm)	no	no	no	no
damaged length (mm)	0	0	0	0
edge reached	no	no	no	no
ignition of cotton wool	no	no	no	no
maximum damaged length (mm)	28	47	32	52
weft	surface ignition		edge ignition	
	1	2	3	4
flame application time (s)	5	15	5	15
afterflame time (s)	0	0	0	0
surface flash	no	no	no	no
propagation length flame surface flash (mm)	0	0	0	0
edge reached	no	no	no	no
ignition of cotton wool	no	no	no	no
maximum damaged length (mm)	29	61	36	65

b. Worst testing conditions - warp (*)

warp	edge ignition				
	1	2	3	4	5
flame application time (s)	15	15	15	15	15
afterflame time (s)	0	0	0	0	0
surface flash	no	no	no	no	no
propagation length flame surface flash (mm)	0	0	0	0	0
edge reached	no	no	no	no	no
ignition of cotton wool	no	no	no	no	no
maximum damaged length (mm)	51	52	57	57	50

Report IMO FTP Code Part 7

Document number:	202302056	Report date:	10/07/2023
Fabric reference:	Obay		
	01-Duckegg (BPZ-012525 BABK)	Date analyses:	10/07/2023
Fabric composition:	100% Polyester inherent FR	Place analyses:	Labotex
Customer:	Verotex Industries	Date of request:	3/07/2023
	Edisonweg 3	Samples received:	3/07/2023
	5466 AR Veghel		
	Netherlands		

Testing and conditioning in standard atmosphere, T (20±2)°C and RH (65±4)%

Specification	Results					Remarks																																																						
<div>c. Worst testing conditions - weft (*)</div> <table> <tr> <td></td> <td colspan="5">edge ignition</td> </tr> <tr> <td>weft</td> <td>1</td> <td>2</td> <td>3</td> <td>4</td> <td>5</td> </tr> <tr> <td>flame application time (s)</td> <td>15</td> <td>15</td> <td>15</td> <td>15</td> <td>15</td> </tr> <tr> <td>afterflame time (s)</td> <td>0</td> <td>0</td> <td>0</td> <td>0</td> <td>0</td> </tr> <tr> <td>surface flash</td> <td>no</td> <td>no</td> <td>no</td> <td>no</td> <td>no</td> </tr> <tr> <td>propagation length flame surface flash (mm)</td> <td>0</td> <td>0</td> <td>0</td> <td>0</td> <td>0</td> </tr> <tr> <td>edge reached</td> <td>no</td> <td>no</td> <td>no</td> <td>no</td> <td>no</td> </tr> <tr> <td>ignition of cotton wool</td> <td>no</td> <td>no</td> <td>no</td> <td>no</td> <td>no</td> </tr> <tr> <td>maximum damaged length (mm)</td> <td>52</td> <td>58</td> <td>52</td> <td>55</td> <td>51</td> </tr> </table> <div>d. Criteria for curtains drapes</div> <ul style="list-style-type: none"> * afterflame time ≤ 5s for any specimen * no flame propagation to the edges for any specimen * no ignition of the cotton wool for any specimen * average char length ≤ 150mm * no occurrence of a surface flash more than 100mm from the point of ignition <div> <div>Pass</div> <div>Fail</div> <div>X</div> </div>								edge ignition					weft	1	2	3	4	5	flame application time (s)	15	15	15	15	15	afterflame time (s)	0	0	0	0	0	surface flash	no	no	no	no	no	propagation length flame surface flash (mm)	0	0	0	0	0	edge reached	no	no	no	no	no	ignition of cotton wool	no	no	no	no	no	maximum damaged length (mm)	52	58	52	55	51
	edge ignition																																																											
weft	1	2	3	4	5																																																							
flame application time (s)	15	15	15	15	15																																																							
afterflame time (s)	0	0	0	0	0																																																							
surface flash	no	no	no	no	no																																																							
propagation length flame surface flash (mm)	0	0	0	0	0																																																							
edge reached	no	no	no	no	no																																																							
ignition of cotton wool	no	no	no	no	no																																																							
maximum damaged length (mm)	52	58	52	55	51																																																							
<div> <div> <div> <div>BELAC</div> <div>364-TEST</div> </div> <div> <div>The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test;</div> <div>they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.</div> </div> </div> </div>																																																												

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.



Annick Gijsemans - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be consulted on the BELAC website https://ng3.economie.fgov.be/Nl/belac/labotesting/applic/accreditedc_nl.asp?certificatienummer=364-TEST

Sampling is performed by the customer. Fabric analysed as received. The results in this report only relate to the tested items.

Samples will be returned to the customer together with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report cannot be copied unless in its complete form and with written approval of Labotex (Kontich).

Uncertainty of measurement on the test result is not taken into account when assessing compliance with the specifications. When results are compliant to the specification, the square next to the result is empty. When the result is not compliant to the specification, the square is filled with a flag "X".

The uncertainty and the description of the methods are available at the lab on request.