

## FLAMMABILITY TEST REPORT

Report No.: LEI19022421A

Date Received: 13/02/19

Date Tested: 25/02/19

Date Issued: 25/02/19

**Company Name & Address:** VEROTEX INDUSTRIES B.V.  
Edisonweg 3  
5466 AR Veghel  
Netherlands

**Contact Name:** IVO JACOBS

### Sample Details

Order No.: Not stated  
Reference No.: Not stated  
Style No.: Not stated  
Batch No.: Not stated  
Quality: XFR Odeon  
Colour: Not stated  
Supplier: Not stated  
Intended Use: Not stated  
Quoted Fibre Composition: Not stated  
Retailer: Not stated  
Buying Division: Not stated  
Sample Description: Red coloured woven fabric

Test Method	Pre Treatment	Flammability Performance Requirement	Result
BS 5867: Part 2: 2008	12 Cycles of BS EN ISO 10528 (Standard Washing Procedure) @ 75°C and then low heat tumble dried.	Type B	PASS
<p><b>Note:</b> In accordance with clause 7 of BS 5867: Part 2: 2008 a fabric for which compliance with the requirements of this standard is claimed shall be supplied with the following information, the manufacturer's name, trademark or other identifying mark, the statement 'Flammability complies with the requirements of BS 5867: Part 2 Type B' and instructions on any special precautions to be taken concerning care (including cleansing) of the product, preferably using an appropriate care labelling symbol in accordance with BS EN ISO 3758 and taking account of the durability procedure used in this test.</p>			

STEVEN OWEN  
(Technical & Operational  
Excellence Manager)

  
ANDREW HALLETT  
(Flammability Team Leader)

CAROLE SPOWART  
(Flammability  
Administrator)

GREGORY JAMES  
(Flammability Technician)

## FLAMMABILITY TEST REPORT

### Test Specification

Test Method: BS 5867: Part 2: 2008 Type B using BS EN ISO 15025: 2002  
(With the modifications from clause 6.3.2 of BS 5867: Part 2: 2008).  
25mm horizontal reach Propane gas flame  
Ignition Source:  
Ignition Type: Surface  
Flame Application Time: 15±1 seconds  
Sample Size: 200 x 160mm  
Side Tested: Face

### Pre-treatment / Durability Procedure

12 Cycles of BS EN ISO 10528 (Standard Washing Procedure) @ 75°C and then low heat tumble dried.

### Conditioning

Prior to Testing: At least 24 hours in an atmosphere having a temperature of 20±2°C. and a relative humidity of 60±5%  
At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 65%

### Test Results

Report of tests carried out in accordance with BS EN ISO 15025:2002. The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

### Test before pre-treatment

Sample No./ Direction	Duration of flaming (Secs)	Duration of afterglow (Secs)	Flaming debris	Flame to edge	Hole to edge	Maximum damaged length (mm)	
						Horizontal	Vertical
1. Length ↑	0.0	0.0	No	No	No	33	77
2. Length ↓	0.0	0.0	No	No	No	21	62
3. Length ↑	0.0	0.0	No	No	No	22	55
4. Width →	0.0	0.0	No	No	No	25	52
5. Width ←	0.0	0.0	No	No	No	23	55
6. Width →	0.0	0.0	No	No	No	21	55

### Test after pre-treatment

Sample No./ Direction	Duration of flaming (Secs)	Duration of afterglow (Secs)	Flaming debris	Flame to edge	Hole to edge	Maximum damaged length (mm)	
						Horizontal	Vertical
1. Length ↑	0.0	0.0	No	No	No	21	90
2. Length ↓	0.0	0.0	No	No	No	22	75
3. Length ↑	0.0	0.0	No	No	No	23	72
4. Width →	0.0	0.0	No	No	No	25	60
5. Width ←	0.0	0.0	No	No	No	24	62
6. Width →	0.0	0.0	No	No	No	23	60

### Conclusions

When tested before and after the durability procedure detailed above the sample meets the flammability performance requirements of BS 5867: Part 2: 2008 Type B. **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.