



Report BS 5867-2 type B

Doc number:	202000563	Report date:	27/02/2020
Quality name:	RE-Juvenate 03-Improved (beige) (DEV1 BAAF)	Date analyses:	27/02/2020
Customer:	VEROTEX Industries Edisonweg 3 5466 AR Veghel Netherlands	Place analyses:	Labotex
		Date test request:	14/02/2020
		Samples received:	14/02/2020

Testing and conditioning in standard atmosphere, T (20+/-2)*C and RH (65+/-4)%

Specification	Results							Remarks	!
Burning behaviour of fabrics for curtains drapes Based on BS 5867, part 2 type B <i>conditioning min 24h. in standard atmosphere</i> <i>sample size: (220 x 170) mm</i> <i>used gas: propane</i> <i>flame height: 40 mm</i> <i>flame application: 15 s</i> <i>surface ignition</i> Method test for: Flame spread: BS EN ISO 15025 Laundering: BS EN ISO 10528	<u>1. Test on original fabric</u>								<input type="checkbox"/>
		warp			weft				
		face	face	reverse	face	face	reverse		
	afterflame time (s)	0.0	0.0	0.0	0.0	0.0	0.0		
	afterglow time (s)	0.0	0.0	0.0	0.0	0.0	0.0		
	edge reached	no	no	no	no	no	no		
	burning debris	no	no	no	no	no	no		
	<u>2. Test on washed fabric</u>								
		warp			weft				
		face	face	reverse	face	face	reverse		
	afterflame time (s)	0.0	0.0	0.0	0.0	0.0	0.0		
	afterglow time (s)	0.0	0.0	0.0	0.0	0.0	0.0		
	edge reached	no	no	no	no	no	no		
	burning debris	no	no	no	no	no	no		
	<u>3. Acceptance criteria</u>								
	No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of sample. If so and if there is no separation of any flaming debris droplets, the fabric shall be deemed to comply with the requirements of this standard.								
	<u>4. Conclusion</u>								
	The fabric's flammability complies with the requirements of BS5867-2 type B.								





Report BS 5867-2 type B

Doc number:	202000563	Report date:	27/02/2020
Quality name:	RE-Juvenate 03-Improved (beige) (DEV1 BAAF)	Date analyses:	27/02/2020
Customer:	VEROTEX Industries Edisonweg 3 5466 AR Veghel Netherlands	Place analyses:	Labotex
		Date test request:	14/02/2020
		Samples received:	14/02/2020

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.

Joeri Neys - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be obtained on request.

The results in this report only relate to the tested items.

Samples will be returned to the customer with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

This report can not be copied unless in its complete form and with written approval of Labotex (Kontich).

Sampling is performed by the customer. Fabric analysed as received.

The uncertainty and the description of the methods are available at the lab on request.