

Verotex Industries BV
Edisonweg 3
5466 AR VEGHEL

Your notice of
28-09-2020

Your reference

Date
30-11-2020

Analysis Report 20.05871.03

Required tests :

ISO 6330 (2000) + A1 (2008), ISO 6330 (2012) **Washing and drying**

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9 **Fire tests - Test for bedding components – smouldering cigarette test**

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9 **Fire tests - Test for bedding components – Match flame equivalent**

Sample id	Information given by the client	Date of receipt
T2020748	XFR-Regalia	28-09-2020



Petra Wittevrongel
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: T2020748 - XFR-Regalia

Washing and drying

Date of ending the test	02-10-2020
Standard used	ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard	-
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	6M- 60°C (2012)
Drying method	F = tumble dry (•) after each washingcycle (2012)
Number of washing cycles	3
Mass of the test specimens	970 g
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2020748_01d



Reference: T2020748 - XFR-Regalia

Fire tests - Test for bedding components – smouldering cigarette test

Date of ending the test 25-11-2020
Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9
Deviation from the standard -
Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Testing substrate Mineral wool fibre pad

Specimen thickness (mm) ≤ 25

Ignition source: smouldering cigarette with the following specifications

Length: (70 ± 4) mm

Diameter: (8.0 ± 0.5) mm


Mass: (0.95 ± 0.15) mm

Smouldering rate: (11.0 ± 4.0) min / 50 mm

Cigarettes on the smooth surface (no stitchings)

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
More than 25 mm from edge of cotton wool	no	no
Smoulders to extremities	no	no
Smoulders through thickness	yes	yes
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass



Reference: T2020748 - XFR-Regalia

Fire tests - Test for bedding components – Match flame equivalent

Date of ending the test 25-11-2020
 Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Testing substrate Mineral wool fibre pad
 Specimen thickness (mm) ≤ 25
 Flame application time (s) 20

Flame on the smooth surface (no stitchings)

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smouldering more than 25 mm from source	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
> 66% consumed	no	no
Burning to the extremities	no	no
Burning through thickness	no	no
Flaming > 150 s	no	no
Afterflame time (s)	0	0
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass