

Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como - Italia
Pho +39 031 331211 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102/154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Test Report No.:

2502687-002

Date Test Report

22-mag-25

Acceptance:

2502687

Arrival date sample

13-mag-25

Start date test

13-mag-25

End date test

22-mag-25

References:

Sampling Mode:

Sampling by Customer *

VEROTEX INDUSTRIES BV

Edisonweg 3

5466 AR VEGHEL

THE NETHERLANDS

Phone: +31 413 342338

[C] Item:

SANDY FR

[C] Declared Composition:

100% PL + FR ACRYLIC

Typology:

fabric

Return:

no requested

Test Results


Test	Method	U.M.	Result
25165 WASHING TREATMENTS	UNI EN ISO 6330:2022		.
Start date test	16/05/2025		
End date test	19/05/2025		
Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS			
Typology of washing machine used: Type A			
Programme of washing: 3N - normal agitation			
Test Temperature: 30°C			
Drying procedure: type C - Flat dry			
Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated - TAED			
Total air-dry- mass (specimens and ballast): 2,0 kg			
Type of ballast used: Type III (polyester)			
Number of washings performed: 01			
THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of CURTAINS AND DRAPES: IGNITABILITY OF VERTICALLY ORIENTED SPECIMENS.			
15386 CURTAINS AND DRAPES:	UNI EN 1101:2006		.
IGNITABILITY OF VERTICALLY ORIENTED SPECIMENS			
Start date test	21/05/2025		
End date test	22/05/2025		
Instrument: Rhoburn Tester			
Pretreatment carried out			N. 1 washing at 30°C
Conditioning of sample			20 ± 2 °C, 65 ± 5 % r.h.
Testing temperature and r.h.			19°C - 63% r.h.
Tested sample surface:			Face
Dimension of specimens:	mm		80x200
Type of gas used:			propane
Type of ignition used:			From the edge

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como - Italia
Pho +39 031 331211 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102/154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2502687-002**


Test	Method	U.M.	Result
MEAN IGNITION TIME			SAMPLE DOES NOT BURN AT 20s OF APPLICATION TIME OF THE FLAME
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			
25165 WASHING TREATMENTS	UNI EN ISO 6330:2022		.
Start date test	19/05/2025		
End date test	21/05/2025		
Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS			
Typology of washing machine used: Type A			
Programme of washing: 3N - normal agitation			
Test Temperature: 30°C			
Drying procedure: type C - Flat dry			
Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated - TAED			
Total air-dry- mass (specimens and ballast): 2,0 kg			
Type of ballast used: Type III (polyester)			
Number of washings performed: 12			
THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of BURNING BEHAVIOUR - CURTAINS AND DRAPES - Measurement of flame spread of vertically oriented specimens with large ignition source.			
15676 BURNING BEHAVIOUR - CURTAINS AND DRAPES - Measurement of flame spread of vertically oriented specimens with large ignition source	UNI EN 13772:2011		.
Start date test	21/05/2025		
End date test	22/05/2025		
Instrument: Rhoburn Tester			
Conditioning of sample			20 ± 2 °C, 65 ± 5 % r.h.
Testing temperature and r.h.			19°C - 63% r.h.
TEST ON SAMPLE IN ITS ORIGINAL STATE:			
- severing of marker threads	-		No
Evidence of flaming debris	-		No
TEST ON REFURBISHED SAMPLE:			
- severing of marker threads	-		No
Evidence of flaming debris	-		No
Deviations from the method			None
Annex n.			2F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como - Italia
Pho +39 031 331211 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102/154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2502687-002**

Test	Method	U.M.	Result
15986 TEXTILES AND TEXTILE PRODUCTS - BURNING BEHAVIOUR - CURTAINS AND DRAPES - CLASSIFICATION SCHEME	EN 13773:2004		
The fabric tested according to standards UNI EN 1101: 2006 "Textiles and textile products. Burning behaviour. Curtains and drapes. Detailed procedure to determine the ignitability of vertically oriented specimens (small flame)" and UNI EN 13772: 2011 "Textiles and textile products. Burning behaviour. Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source"			
MEETS THE REQUIREMENTS OF CLASS 1 according to the UNI EN 13773: 2004 "Textiles and textile products - Burning behavior - Curtains and drapes - Classification scheme"			

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

Page 3 di 3