



Verotex Industries BV
Edisonweg 3
5466 AR VEGHEL

Your notice of
 03-02-2020

Your reference

Date
 14-02-2020

Analysis Report 20.00629.01

Required tests :

- IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8** **Fire tests - Test for upholstered furniture - smouldering cigarette test**
- IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8** **Fire tests - Test for upholstered furniture - Match flame equivalent**

Identification number	Information given by the client	Date of receipt
T2002416	Moon	03-02-2020



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

INRICHTING ERKENND BIJ TOEPASSING VAN: DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTÉ-LOI DU 30 JANVIER 1947



CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be
 GENT • Technologiepark 70 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
 GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
 KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 29 27 00 • fax +32 56 29 27 01 • info@vkc.be
 VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB



Reference: T2002416 - Moon

IMO upholstered furniture


Information given by the client

Type of furniture

Upholstery

Fabric

Composition	100% polyester FR
Structure	Weave
Number of threads - warp	11+11/cm
Number of threads - weft	23.5/cm
Yarn count - warp	300D+300D
Yarn count - weft	300D
Thickness in mm	0.620
Weight g/m ²	415
Colour	Red
Inherently FR treated	yes



Reference: T2002416 - Moon

Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test	13-02-2020
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - $\pm 36 \text{ kg/m}^3$

Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$

Diameter: $(8.0 \pm 0.5) \text{ mm}$

Mass: $(0.95 \pm 0.15) \text{ mm}$

Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$



	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
	non-ignition	non-ignition

Conclusion Pass



Reference: T2002416 - Moon

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test 13-02-2020
 Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - ± 36 kg/m³

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
	non-ignition	non-ignition

Conclusion Pass